

TECHNICAL DATA SHEET

JOKISCH KORIA NEFO 06.00 (Jokisch Corrosion Protection Oil DW)

Film forming corrosion protection oil, with excellent water displacing properties.

APPLICATION

Preservation of semifinished and finished products between working operations. The thin film also protects against contact corrosion and humidity, as well as final preservation of indoor storage. The product can be applied either by dipping, brushing or spraying.

CHARACTERISTICS

- Very good wetting properties
- High spray water resistance
- Easy to degrease
- High aging stability
- Long storage capability without resinification

CORROSION PROTECTION TIME

Indoor storage: 6 months
Outdoor storage: 0 months

TECHNICAL SPECIFICATIONS

	UNIT	METHOD	JOKISCH KORIA NEFO 06.00
Kin. viscosity at 40°C	mm ² /s	ASTM D 7042	5
Density at 20°C	g/cm ³	DIN 51 757	0,81
Flash point	°C	DIN 51 755	62
Vapour pressure at 20°C	hPa	-	~0,5
Ignition temperature	°C	-	>200
Salt spray test		ASTM B117 DIN EN ISO 9227	24h= R-0 48h= R 0-1 120h= R-2

This information is based on the latest state of knowledge. They are intended to describe the product and thus do not have the meaning to assure certain properties. A liability can not be derived from this.

STORAGE

Storage temperature: 5 – 40°C
Storage time: 36 months

Jokisch GmbH
Fabrik für Schmier- und Kühlmittelspezialitäten

Industriestraße 5-10 | 33813 Oerlinghausen
T +49 52 02 97 34 0 | F +49 52 02 97 34 49
info@jokisch-fluids.de | www.jokisch-fluids.de

